CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	CP-2019-05-23-58 **Date: 25/04/2019**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.
Agency	:	Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.
Customer's Reference	:	EE/DD/WO/340/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-04-2019
Customer ID	:	Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	25/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Lintel Concrete	M25	18/04/2019	25/04/2019	150.91 X 151.47 X 149.11	22859	8.326	547.6	24.0	23.0
2	Lintel Concrete	M25	18/04/2019	25/04/2019	150.29 X 151.28 X 149.10	22737	8.700	517.6	22.8	
3	Lintel Concrete	M25	18/04/2019	25/04/2019	150.64 X 149.24 X 151.58	22482	8.048	501.6	22.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID	:	**CP-2019-05-23-58**
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.
Agency	:	Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.
Customer's Reference	:	EE/DD/WO/340/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-04-2019
Customer ID	:	Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/05/2019

Date: 16/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Lintel Concrete	M25	18/04/2019	16/05/2019	151.63 X 151.42 X 151.06	22961	**8.851**	624.6	27.2	
2	Lintel Concrete	M25	18/04/2019	16/05/2019	149.29 X 149.48 X 149.35	22316	**8.948**	581.9	26.1	27.4
3	Lintel Concrete	M25	18/04/2019	16/05/2019	149.53 X 151.73 X 149.87	22688	**8.578**	652.9	28.8	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/04/2019

Lab ID	:	CP-2019-05-23-58
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.
Agency	:	Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.
Customer's Reference	:	EE/DD/WO/340/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-04-2019
Customer ID	:	Chejja Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	25/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Chejja Concrete	M20	18/04/2019	25/04/2019	149.24 X 151.60 X 149.25	22624	8.749	418.3	18.5	18.4
2	Chejja Concrete	M20	18/04/2019	25/04/2019	151.92 X 151.97 X 149.53	23088	8.901	416.8	18.1	
3	Chejja Concrete	M20	18/04/2019	25/04/2019	149.68 X 151.34 X 150.07	22652	8.615	419.4	18.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-05-23-58

Date: 16/05/2019

Customer : Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.

Address : Shettyhalli Sub Division, BBMP, Bangalore.

Project Name : Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.

Agency : Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.

Customer's Reference : EE/DD/WO/340/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-04-2019

Customer ID : Chejja Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Chejja Concrete	M20	18/04/2019	16/05/2019	151.91 X 151.72 X 150.35	23049	8.634	531.8	23.1	23.0
2	Chejja Concrete	M20	18/04/2019	16/05/2019	150.25 X 151.68 X 150.78	22790	8.185	516.7	22.7	
3	Chejja Concrete	M20	18/04/2019	16/05/2019	150.91 X 150.42 X 151.39	22700	8.345	527.4	23.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 12/04/2019

Lab ID	:	CP-2019-05-23-58
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.
Agency	:	Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.
Customer's Reference	:	EE/DD/WO/340/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-04-2019
Customer ID	:	Sump Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	12/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Sump Bottom Slab Concrete	M25	05/04/2019	12/04/2019	151.60 X 150.11 X 151.21	22756	8.326	540.2	23.7	23.1
2	Sump Bottom Slab Concrete	M25	05/04/2019	12/04/2019	150.95 X 151.06 X 151.86	22802	8.700	522.2	22.9	
3	Sump Bottom Slab Concrete	M25	05/04/2019	12/04/2019	151.21 X 150.39 X 150.87	22741	8.048	516.2	22.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-05-23-58 **Date: 03/05/2019**

Customer : Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.

Address : Shettyhalli Sub Division, BBMP, Bangalore.

Project Name : Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.

Agency : Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.

Customer's Reference : EE/DD/WO/340/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-04-2019

Customer ID : Sump Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Sump Bottom Slab Concrete	M25	05/04/2019	03/05/2019	149.97 X 149.42 X 151.84	22410	**8.851**	618.4	27.6	27.7
2	Sump Bottom Slab Concrete	M25	05/04/2019	03/05/2019	149.53 X 149.01 X 150.10	22281	**8.948**	598.6	26.9	
3	Sump Bottom Slab Concrete	M25	05/04/2019	03/05/2019	150.54 X 150.07 X 150.24	22591	**8.578**	649.4	28.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 12/04/2019

Lab ID	:	CP-2019-05-23-58
Customer	:	Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.
Address	:	Shettyhalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.
Agency	:	Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.
Customer's Reference	:	EE/DD/WO/340/18-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-04-2019
Customer ID	:	Sump Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	12/04/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Sump Side Wall Concrete	M25	05/04/2019	12/04/2019	150.93 X 149.77 X 150.95	22605	8.326	525.2	23.2	22.8
2	Sump Side Wall Concrete	M25	05/04/2019	12/04/2019	149.90 X 149.10 X 151.04	22350	8.700	497.3	22.2	
3	Sump Side Wall Concrete	M25	05/04/2019	12/04/2019	149.78 X 150.41 X 149.65	22529	8.048	517.0	22.9	

Note:
1. The results pertain to the samples received and tested.
2. All information furnished by Customer/Representative
3. Any correction in the report will make this report invalid
4. This report without prior written approval should not be reproduced or published in full or part.
5. Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig. Date

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : CP-2019-05-23-58

Date: 03/05/2019

Customer : Assistant Executive Engineer, Shettyhalli Sub Division, BBMP, Bangalore.

Address : Shettyhalli Sub Division, BBMP, Bangalore.

Project Name : Construction of General Public Toilet in Mallasandra Colony School in Ward No.13 Shettyhalli Sub Division.

Agency : Sri.Muniraj Naik, #58 Rayan Nagara, Nelamanaga, Bangalore-562123.

Customer's Reference : EE/DD/WO/340/18-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-04-2019

Customer ID : Sump Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Sump Side Wall Concrete	M25	05/04/2019	03/05/2019	151.18 X 151.95 X 149.48	22971	**8.851**	631.8	27.5	27.8
2	Sump Side Wall Concrete	M25	05/04/2019	03/05/2019	151.52 X 151.89 X 150.90	23014	**8.948**	619.2	26.9	
3	Sump Side Wall Concrete	M25	05/04/2019	03/05/2019	150.12 X 149.12 X 150.94	22387	**8.578**	647.5	28.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner